

Product name	Ceramic fiber fabric with fiberglass			
Product size	2mm*1000mm*30m			
Test item	Content,loss on ignition, Temperature resistance and so on	warp and weft density	10cm*10cm	
Test item name	Standard requirements	Test result	Test conclusion	error value
Volume density kg/m²	500	500	qualified	±0.5
Width	1000	1000	qualified	±0.2
Length	30	30	qualified	±0.2
Warp density	48---60	59	qualified	±0.2
Weft density	21---30	23	qualified	±0.2
rate of water content%	≤2	1.8	qualified	
rate of Ceramic fiber content	75-85	80	qualified	±0.5
rate of fiberglass content	10	10	qualified	
rate of viscose rayon content	10	10	qualified	
Temperature resistance	650℃---1000℃	800℃	qualified	±100
loss on ignition	≤15	14	qualified	±0.2