

CERAMIC FIBERGLASS CLOTH SS 2 MM

Name	Cerami	c fiber clot	h	Style		TCR2800S-2-1-30		
Date	201	3-11-01	Test Date		te	2013-11-05		
			Test I	nd <mark>ex &</mark> Item				
Sril	Item		Stan <mark>dard</mark>			Actual	Result	
1	Thickness		2mm ±0.1mm			2mm	Qualified	
2	Width		1000 ±1mm			1000mm	Qualified	
3	Density		550kg/m3 ±10%			525kg/m3	Qualified	
4	Tensile strength Warp X Weft 50mm/n		≥600×400			605×400	Qualified	
5	Count of	Warp	58 ±1 END/CM			58 END/CM	Qualified	
	yarn	Weft	29 ±1 END/CM			30 END/CM	Qualified	
6	Loss on ignition		<u>≤18%</u>			14%	Qualified	
7	Chemical composition							
	Al2O3 Fe2O3 CaO+Na2O		45~48% 0.7~1.2% 0.43%			47% 1.0% 0.43%	Qualified	
8	Standa	ard		GB/T3303-2006				

U1, F1, No.1, In front of the Ferdowsi Grand Hotel, Fersowsi St., Tehran, Iran Tel:+9821 33993093 +9821 36612593 9+98922 347 1416

